



## **SPECIFICATION**

<b>RADIANT COATING</b>
<b>OKITSUMO COOLTECH</b>
<b>CT- 600 BLACK</b>

ADAPT TEMP. : 400 - 600	DRYING : Baking	1 coat type
COLOR : Black	Mat type	PACKING : 1 Liquid type

### **CHARACTERISTIC**

It does not change the quality of radiation in use at high temperature.  
It has excellent adhesion.

### **APPLICATION**

Iron, stainless

### **COATING METHOD**

SURFACE PREPARATION		Degreasing or blast
WAY OF COATING		Spray or electrostatic coating
DILUENT	Spray	50B, 100B thinner
	Electrostatic	0.6, 0.7, 0.8 thinner
DILUTION	Spray	20 - 40 wt%
	Electrostatic	20 - 50 wt%
THICKNESS (DRY)		35 - 50 $\mu$ m
COATING TIMES		1 time
STANDARD BUDGET		300g/m <sup>2</sup> /time
SETTING		80 - 100 $\times$ 10mins.
DRYING		180 $\times$ 20mins.

\* For repair, remove the dust with sand paper (#600-#1000), then recoat and baking.

**PACKING** 1Kg, 4Kg, 16Kg