



SPECIFICATION

Okitsumo coating for muffler **MF4-S**

HEAT RESISTANCE : 650	DRYING : Baking	1 coat type
COLOR : Silver	Mat type	PACKING : 1 Liquid type

CARACTERISTIC

It excels in heat resistance, corrosion resistance, gasoline resistance and chemical resistance.

MATERIAL Iron

APPLICATION Muffler for automobile

COATING METHOD

SURFACE PREPARATION	Degreasing or blast
WAY OF COATING	Spray
DILUENT	50, 100 thinner
DILUTION	0 - 20wt%
THICKNESS (DRY)	10 - 20 μ m
COATING TIMES	1 time
SUITABLE AMOUNT	150g/m ² /time
SETTING	5 - 20mins.
DRYING	180 \times 20mins.

* For repair, remove the dust with sand paper (#600-#1000), then recoat and baking.

PACKING 800g, 3Kg, 16Kg