



SPECIFICATON

B7

仕 1-NA501BL-001

**Okitsumo Fluororesin Paint
navalon
NA501BL**

Heat Resistace	250	Drying	Baking	Construction	1 Coat
Color	Black	Luster	Half-gloss	Packing	1 Liquid

CHARACTERISTIC This is one coat type and non adhesive, adhesion and corrosion resistance so that balanced item.
It excels in adhesion to stainless. (No need to blast)

MATERIAL Aluminum, Stainless, Galvanized steel plate, Aluminizing steel plate.

APPLICATION Inside of frying pan, top plate of gas stove, iron base, cake mold, louver of fan heater.

COATING SPECIFICATION

PREPARATION	Degreasing	
COATING METHOD	Spraying, electrostatic coating (1)	
DILUTION	SPRAY	4 4 7 6 thinner
	ELECTROSTATIC	6 8 0 5 thinner
DILUENT	SPRAY	0 ~ 10wt%
	ELECTROSTATIC	10 ~ 30wt%
STANDARD FILM THICKNESS (Dry)	10 ~ 20 μm	
COATING TIMES	1time	
STANDARD QTY. OF COATING	200g / m ² / time	
PREDRYING	80 ~ 100 × 10min.	
DRYING	380 × 15min (2)	

(1) Mix the paint before use and re-disperse.

(2) It generates gasification fluorine compound so that please ventilate well.

* When repair it, remove the coating film by blast completely, then re-coat , drying and baking.

PACKAGE 1Kg, 4Kg, 16Kg