



# Specification

Issued :2007.5.23  
Revised :2007.7.26

## Okitsumo Heat resistant paint (for 600 ) BOSE Neos for General specification

### Painting by brush

Process	Product Name	Blending Base : Hardener [Working life]	Diluent	Dilution (wt%)	Coverage (g/m <sup>2</sup> /pass)	Fiml thickness Dry (μm)	Interval (20 )	
1	Appropriate substrate	Ordinary steel plate, Forged steel plate, stainless steel plate, etc.						
2	Pre-treatment	Over SSPC-SP3/SIS St3 (by hand tool, machine tool or blast)						
5	Primer	BOSE Neos ZR Rust Primer	-	Neos01 Thinner	0 ~ 10	170	20	Over 1Hr Within 7 days
6	Top coat	BOSE Neos S-600 Silver	-	Neos02 Thinner	0 ~ 10	85	10	-

### Painting by airless

Process	Product Name	Blending Base : Hardener [Working life]	Diluent	Dilution (wt%)	Coverage (g/m <sup>2</sup> /pass)	Fiml thickness Dry (μm)	Interval (20 )	
1	Appropriate substrate	Ordinary steel plate, Forged steel plate, stainless steel plate, etc.						
2	Pre-treatment	Over SSPC-SP3/SIS St3 (by hand tool, machine tool or blast)						
4	Primer	BOSE Neos ZR Rust Primer	-	Neos01 Thinner	10 ~ 20	190	20	Over 1Hr Within 7 days
5	Top coat	BOSE Neos S-600 Silver	-	Neos02 Thinner	0 ~ 10	95	10	-

#### [Drying]

Drying at room temperature make the film half-cure. For reference, harden at 180 for 20mins by baking.